
Technical Instruction Sheet

Page 1 of 1

Properties:

AKEMI® Rallye Sprays are high-quality, one-component paints which contain solvents. They do not contain CFC propellants. These products are characterised by the following properties:

- fast-drying
- very good covering power
- very good adhesion to iron, steel, wood and light metal alloys
- weather resistant and does not yellow
- high surface hardness but nevertheless good elasticity
- can be polished
- free of lead and CFCs
- resistant to petrol and thawing salt as well as the car wash

Application areas:

AKEMI® Rallye Sprays are used to improve the appearance of cars and can also be used in the domestic sector and for hobby purposes.

Instructions for use:

1. The surface must be free of rust, oil and grease, must be thoroughly clean, dry and slightly abraded. Inactivate residual rust with AKEMI® Rust Converter and then apply AKEMI® Zinc Spray.
2. If the undersurface is not of the same nature, prime the surface first using AKEMI® Primer – light grey.
3. Shake the spray can vigorously before use (you can hear the mixing balls).
4. Parts which are not to be sprayed must be masked or covered with paper.
5. Apply several thin layers (at a spraying distance of approx. 25 cm and at intervals of 3-5 minutes)

Special remarks:

- Use AKEMI® "Liquid Glove" in order to protect your hands.
- Do not use at too high temperatures or in intense sunlight because the paint dries too quickly and does not run properly (formation of haze). 15-25° C is the best working temperature.
- The product dries much better if it is applied in several thin coats instead of one thick layer only.
- The spray nozzle does not have to be emptied of paint when your work is done.
- Parts which have been sprayed by mistake can be cleaned with AKEMI® Universal Dilution (compatibility check first!)

Safety notices:

Please refer to the EC safety data sheet

Technical specifications:

colour:	black (matt, silk gloss, gloss) white gloss
density:	approx. 0.8 g/cm ³
drying:	dust does not cling after approx. 14 minutes tack-free after 25 minutes firm after approx. 50 minutes thoroughly dry and capable of being polished after approx. 24 hours
coverage:	approx. 1.3 m ² per spray can
shelf life:	can be stored for approx. 1 year in the closed original container under cool and frost-free conditions.

Notice:

The above information is based on the latest stage of our development and application technology. Due to a multiplicity of different influencing factors, this information – as well as other oral or written technical advises – must be considered as non-binding hints. The user is obliged in each particular case to conduct performance tests, including but not limited to trials of the product, in an inconspicuous area or fabrication of a sample piece.

TIS 01.03